## Kotex Polycarbonate

型号: K-75E 板材 颜色: 原色、高粘性

4±. 44-	加州十十分	知中子 十二 7分:	<b>光</b>	*\-\-\-\-\-\-\-\-\-\-\-\-\-\-\-\-\-\-\-
特性	测定方法	测定标准	单位	数据
机械特性				
Izod 冲击强度		23°C V-notched 1/8"	J/m	880
	ASTM D256		kgf-cm/cm	90
			ft·lbf/in	17
拉伸强度			MPa	63
	ASTM D638		kgf/cm <sup>2</sup>	640
			lbf/in <sup>2</sup>	9100
断裂伸长度	ASTM D638		%	120
弯曲强度			MPa	85
	ASTM D790		kgf/cm <sup>2</sup>	870
			lbf/in <sup>2</sup>	12400
弯曲模量			MPa	2200
	ASTM D790		kgf/cm <sup>2</sup>	22500
			lbf/in <sup>2</sup>	319000
热特性				
熔体流动率	ASTM D1238	300°ℂ, 1.2kgf	g/10min	4
热变形温度	ASTM D648	18.6 kgf/cm <sup>2</sup>	$^{\circ}\!\mathbb{C}$	135
			°F	275
电力特性				
绝缘强度	ASTM D149	1.6mm	kV/mm	20
电容率	ASTM D150	10 <sup>6</sup> Hz		2.9
介电损耗因子	ASTM D150	10 <sup>6</sup> Hz		0.009
弧阻	ASTM D495		Sec.	110
体积电阻率	ASTM D257		Ω•cm	10 <sup>16</sup>
光学特性				
透光系数	ASTM D1003	3 mm	%	89
光折射率	ASTM D542			1.58
模糊	ASTM D1003	3 mm	%	< 1
物理特性				
比重	ASTM D792			1.2
吸水性	ASTM D570	24小时23 ℃浸水	%	≦ 0.2
模具收缩	ASTM D955		%	0.5~0.7
燃烧性	UL94			V-2 @ 1.6mm

To our best knowledge, the values contained herein are typical of uncoloured PC and given in good faith. They may be affected by colorants, other additives, the design of a mould/die, moulding techniques applied, the size and shape of a moulded article. In view of these factors, the properties do not relieve customers from carrying out their own investigations and tests. It is entirely the customer's responsibility to determine the suitability of material and grade used for their intended application. No warranty, express or implied is made nor is liability accepted in connection with any of the information provided. We reserve the right to make additions, deletions, or modifications to the information at any time without prior notification. Kotec Corporation (30.3.2009)